

TEST REPORT

Test Report # 16H-08729 Date of Report Issue: December 20, 2016
Date of Sample Received: December 13, 2016 Pages: Page 1 of 6

CLIENT INFORMATION:

Company: Shenzhen Ruixin Glassware Co., Ltd
Recipient: Daisy Huang
Recipient Email: sales08@srxglassware.com



SAMPLE INFORMATION:

Description:	Wine glass	Purchase Order Number:	RXDA161207
Assortment:	-	Toy Co./Agency:	-
SKU/style No.:	602001, 602002	Country of Origin:	China
Factory/Supplier/Vendor:	-	Labeled Age Grade:	-
Country of Distribution:	Europe	Recommended Age Grade:	-
Quantity Submitted:	4 pcs per style	Tested Age Grade:	-
Testing Period:	12/13/2016 – 12/20/2016		

OVERALL RESULT:

 **PASS**

Refer to page 2 for test result summary and appropriate notes.

ANSECO GROUP (HK) LIMITED



Vincent Chow Wai Kit
Manager, Chemical Laboratory

ANSECO GROUP (HK) LIMITED • 3/F Liven House • No. 61 – 63 King Yip Street • Kwun Tong • Kowloon • Hong Kong • Tel: (852)3185 8000

The above test(s) is/are accredited under the laboratory's ISO/IEC 17025 accreditation issued by the ANSI-ASQ National Accreditation Board (ANAB) according to certificate and scope of accreditation (Certificate # AT-1500.) Test(s) marked with '#' is/are not covered under the scope of accreditation.

The test result(s) and conclusion(s) in this report relate to the sample(s) tested as described herein.

This test report may not be reproduced in whole or in part, without written approval of ANSECO Group (HK) Limited.

ANAB is recognized by ILAC, APLAC and IAAC as a signatory of multilateral recognition arrangements that facilitate acceptance of test internationally.

TEST RESULTS SUMMARY:

At the request of the client, the following test was conducted:

CONCLUSION	TEST(S) CONDUCTED
PASS	EC Directive 84/500/EEC as amended by Directive 2005/31/EC, Release of Lead and Cadmium from Ceramic Articles

DETAILED RESULTS:

EC Directive 84/500/EEC as amended by Directive 2005/31/EC, Release of Lead and Cadmium from Ceramic Articles

Test Method: EN 1388-1:1995 and/or EN 1388-2:1996

Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	1A	1B	1C	1D	Average (mg/L)	Limit (mg/L)
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)		
Volume of Acid Used, mL	430	430	430	430		
Leachable Cadmium (Cd)	ND	ND	ND	ND	NA	0.3
Leachable Lead (Pb)	ND	ND	ND	ND	NA	4.0
Conclusion	PASS	PASS	PASS	PASS		

Note:

mL = Millilitres

mg/L = Milligrams per litre

NA = Not applicable

LT = Less than

ND = Not detected (Reporting Limit: Cd = 0.02 mg/L; Pb = 0.04 mg/L)

Category		Leachable Cd	Leachable Pb
	1: Articles which cannot be filled and articles which can be filled, the internal depth of which, measured from the lowest point to the horizontal plane passing through the upper rim, does not exceed 25mm	0.07 mg/dm²	0.8 mg/dm²
X	2: All other articles which can be filled	0.3 mg/L	4.0 mg/L
	3: Cooking ware; packaging and storage vessels having a capacity of more than three litres	0.1 mg/L	1.5 mg/L
	4. Drinking rim	0.2 mg/item	2 mg/item

DETAILED RESULTS:

EC Directive 84/500/EEC as amended by Directive 2005/31/EC, Release of Lead and Cadmium from Ceramic Articles

Test Method: EN 1388-1:1995 and/or EN 1388-2:1996
Analytical Method: Inductively Coupled Plasma-Optical Emission Spectrometry

Specimen No.	2A	2B	2C	2D	Average (mg/L)	Limit (mg/L)
Test Item	Result (mg/L)	Result (mg/L)	Result (mg/L)	Result (mg/L)		
Volume of Acid Used, mL	550	550	550	550		
Leachable Cadmium (Cd)	ND	ND	ND	ND	NA	0.3
Leachable Lead (Pb)	ND	ND	ND	ND	NA	4.0
Conclusion	PASS	PASS	PASS	PASS		

Note:

mL = Millilitres

mg/L = Milligrams per litre

NA = Not applicable

LT = Less than

ND = Not detected (Reporting Limit: Cd = 0.02 mg/L; Pb = 0.04 mg/L)

Category		Leachable Cd	Leachable Pb
	1: Articles which cannot be filled and articles which can be filled, the internal depth of which, measured from the lowest point to the horizontal plane passing through the upper rim, does not exceed 25mm	0.07 mg/dm²	0.8 mg/dm²
X	2: All other articles which can be filled	0.3 mg/L	4.0 mg/L
	3: Cooking ware; packaging and storage vessels having a capacity of more than three litres	0.1 mg/L	1.5 mg/L
	4. Drinking rim	0.2 mg/item	2 mg/item

SPECIMEN DESCRIPTION:

Specimen No.	Specimen Description	Location
1	Transparent glass	Wine glass (small style)
2	Transparent glass	Wine glass (large style)

SAMPLE PHOTO:



-End Report-